

# Accelerator NL-49P

Cobalt(II) 2-ethylhexanoate

Solution of 1% cobalt in solvent mixture used for curing UP resins at ambient temperatures.

CAS number  
136-52-7

EINECS/ELINCS No.  
205-250-6

TSCA status  
listed on inventory

## Specifications

Appearance	Clear brown liquid
Cobalt	0.95-1.05 %

## Characteristics

Density, 20 °C	0.949 g/cm <sup>3</sup>
Viscosity, 20 °C	7 mPa.s

## Applications

The curing of unsaturated polyester resins at ambient temperatures can in general not be performed by an organic peroxide alone. The radical formation, which is necessary to start the polymerization reaction, is at ambient temperatures with most generally applied organic peroxides too slow. To speed up the radical formation in a controllable way organic peroxides must therefore be used in combination with a so-called accelerator. For ketone peroxides like methyl ethyl ketone peroxides, cyclohexanone peroxides and acetylacetone peroxide a cobalt accelerator must be used.

## Storage

Accelerator NL-49P is stable at ambient temperatures.

### Note

When stored under these recommended storage conditions, Accelerator NL-49P will remain within the Nouryon specifications for a period of at least 9 months after delivery.

## Packaging and transport

The standard packaging is a 25 kg and 200 kg drum. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Accelerator NL-49P is not classified as a dangerous good according to national and international transport regulations.

## Safety and handling

Keep containers tightly closed. Store and handle Accelerator NL-49P in a dry well-ventilated area at ambient temperatures. Do not mix with organic peroxides. Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Accelerator NL-49P. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at <https://polymerchemistry.nouryon.com>.

## Major decomposition products

In a fire, cobalt oxides and carbon monoxide may be formed.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Trigonox, Butanox and Cyclonox are registered trademarks of Nouryon Chemicals B. V. or affiliates in one or more territories.

## Contact Us

**Europe, Middle East, India and Africa**  
[polymerchemistry.nl@nouryon.com](mailto:polymerchemistry.nl@nouryon.com)

**Asia Pacific**  
[polymerchemistry.ap@nouryon.com](mailto:polymerchemistry.ap@nouryon.com)

**Americas**  
[polymerchemistry.na@nouryon.com](mailto:polymerchemistry.na@nouryon.com)

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, sans-serif font, all in orange.