

BERMOCOLL CCA 470

Ethyl hydroxyethyl cellulose

BERMOCOLL CCA 470 is a strong modified nonionic, water soluble cellulose ether, intended as a water retaining and consistency improving additive to gypsum based mortars.

Specifications

Appearance	Whitish powder
Particle size	98 % ≤ 350 μm
Water content	≤ 4 %

Characteristics

Surface activity	Weak
Viscosity at 20 °C (Brookfield LV), 1% solution	2500-3500 mPa.s

Notes:

Bermocoll® CCA 470 is a modified, high viscosity grade of ethyl hydroxyethyl cellulose.

Applications

Bermocoll® CCA 470 is used in gypsum based mortars to improve the workability, consistency and water retention. Bermocoll® CCA 470 provides high sag resistance.

Storage

In unopened bags, Bermocoll® CCA 470 can be stored for several years. In opened bags, the moisture content of Bermocoll® CCA 470 will be influenced by the air humidity.

Packaging and transport

Like many industrial processed powdery materials, cellulose ether dusts are combustible and can cause dust explosions. Dust formation must be avoided or kept to a minimum. Care should be taken to prevent ignition from heat, spark, open flames or hot surface. BERMOCOLL CCA 470 is packed in a polyethylene bag. Net weight 20 kg. We recommend emptying the bags from the bottom. The empty bags can be recycled and burned. In unopened bags, BERMOCOLL CCA 470 can be stored for several years. In opened bags, the moisture content of BERMOCOLL CCA 470 will be influenced by the air humidity. At the temperatures above 250°C (480°F), charring of BERMOCOLL CCA 470 will occur. At high temperatures and in contact with an open flame, BERMOCOLL CCA 470 will burn slowly with the characteristics of cellulose.

Safety and handling

Bermocoll® CCA 470 should be admixed to the mortar in dry form. At the temperatures above 250 °C (480 °F), charring of Bermocoll® CCA 470 will occur. At high temperatures and in contact with an open flame, Bermocoll® CCA 470 will burn slowly with the characteristics of cellulose.

Certifications

Nouryon Chemicals AG has been certified according to ISO 9001, ISO 14001 and OHSAS 18001.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Bermocoll® is a registered trademark of Nouryon For more information, please visit our website at www.nouryon.com.

The logo for Nouryon, featuring a stylized blue 'N' followed by the word 'ouryon' in a blue sans-serif font.