

TEAL SSG

Triethylaluminum

TEAL SSG is an aluminum precursor (Select Semiconductor Grade) for deposition technologies used in the silicon semiconductors industry.

CAS number
97-93-8

EINECS/ELINCS No.
202-619-3

TSCA status
listed on inventory

Molecular weight
114.2

Characteristics

Appearance	Clear, colorless liquid
Boiling point, 760 torr	186 °C
Density, 30 °C	0.832 g/cm ³
Melting point	-52 °C
Solubility	Soluble in aromatic and saturated aliphatic and cycloaliphatic hydrocarbons
Stability to air	Ignites upon exposure
Stability to water	Reacts violently, may ignite upon contact
Viscosity, 30 °C	2.5 mPa.s

Vapor Pressure

at 10 °C / 283.15 K	4.87 torr
at 15 °C / 288.15 K	6.57 torr
A	2134
B	8.224
Gas constants	$\log P(\text{torr}) = B - A/T(K)$

Thermochemical properties

Heat of vaporization ΔH_v , 127 °C / 1 bar	536 J/g (128 cal/g)
Specific heat, 57 °C	2.226 J/g.°C (0.532 cal/g.°C)
Heat of formation ΔH_f° , 25 °C / 1 bar	-218 kJ/mole (-52 kcal/mole)
Heat of combustion ΔH_c° , 25 °C	-5104 kJ/mole (-1220 kcal/mole)

Applications

TEAL SSG is used as a high quality aluminum precursor for atomic layer deposition (ALD) processes in the silicon semiconductor industry. Containers are fabricated from stainless steel with an electropolished internal finish and are equipped with dip tube for top discharge and diaphragm valves. The diaphragm valves are equipped with metal gasket face seal connections.

Storage

TEAL SSG is stable when stored under a dry, inert atmosphere and away from heat. CAUTION: TEAL SSG may undergo violent exothermic decomposition with flammable gas evolution if stored at temperatures above 70°C (158°F) (see section on Safety and handling).

Packaging and transport

Containers are fabricated from carbon steel and are equipped with dip tubes for top discharge and all connections are located in the vapor space. Valves are equipped with standard VCR connections. For more information please refer to our Cylinder Offerings leaflet, available at www.Nouryon.com/hpmo. Both packaging and transport meet the international regulations. TEAL SSG is classified as Organometallic substance, liquid, pyrophoric, water-reactive; Class 4. 2; UN 3394; PG I

Safety and handling

TMAL SSG ignites upon exposure to air and reacts violently with water. Water must be scrupulously removed from process equipment prior to putting it into metal alkyls service. Failure to do so may result in an explosion. If heated above 120°C (248°F), TMAL SSG will undergo exothermic decomposition with evolution of flammable gas. Products of complete combustion of TMAL are aluminum oxide, carbon dioxide and water. TMAL SSG causes severe burns to the skin and eyes. It is imperative that proper personal protective equipment be worn when handling TMAL SSG. Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of TEAL SSG. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at <https://hpmo.nouryon.com>.

Additional information

Nouryon uses leading edge processes, purification and transfilling techniques that ensure the repeatable and consistent delivery of our TEAL SSG in each cylinder that we supply. We apply state of the art techniques such as ICP-OES for trace metal analysis to meet your demands. Please contact us for detailed sales specifications.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Swagelok and VCR are registered trademarks of Swagelok Company.

Contact Us

Polymer Catalysts Americas
polymer.amer@nouryon.com

Polymer Catalysts Europe, Middle East, India and Africa
polymer.emeia@nouryon.com

Polymer Catalysts Asia Pacific
polymer.apac@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font. The 'N' is significantly larger and more prominent than the rest of the text.