


# Trigonox SBP

Di-sec-butyl peroxydicarbonate



Initiator for (co)polymerization of ethylene, vinyl chloride and vinylidene chloride.

CAS number  
19910-65-7

EINECS/ELINCS No.  
243-424-3

TSCA status  
listed on inventory

## Specifications

Active oxygen	≥6.69 %
Appearance, -20 to -10 °C	Clear liquid
Assay	≥98.0 %
Inorganic + organic hydrolysable chloride	≤100 mg/kg

## Characteristics

Density	1.06 (at 5°C ) g/cm <sup>3</sup>
---------	----------------------------------

## Applications

Trigonox SBP is an efficient initiator for the production of Low Density Polyethylene (LDPE). It is used both for tubular and autoclave processes. In most cases a combination with other peroxides is used to ensure a broad reactivity range.

Trigonox SBP may be applied as an initiator for the suspension polymerization of vinyl chloride in the temperature range of 40-65°C

## Half-life data

The reactivity of an organic peroxide is usually given by its half-life ( $t_{1/2}$ ) at various temperatures. The half-life of Trigonox SBP in chlorobenzene is:

0.1 hr	at 82°C (180°F)
1 hr	at 63°C (145°F)
10 hr	at 47°C (117°F)
Formula 1	$k_d = A \cdot e^{-E_a/RT}$
Formula 2	$t_{1/2} = (\ln 2) / k_d$
Ea	123.85 kJ/mole
A	3.19E+15 s <sup>-1</sup>
R	8.3142 J/mole·K
T	(273.15+°C) K

## Thermal stability

0°C (32°F)

Emergency temperature ( $T_e$ )	10°C (14°F)
Control temperature ( $T_c$ )	20°C (-4°F)
Method	The Heat Accumulation Storage Test is a recognized test method for the determination of the SADT of organic peroxides (see Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria - United Nations, New York and Geneva).

## Storage

Due to the relatively unstable nature of organic peroxides a loss of quality can be detected over a period of time. To minimize the loss of quality, Nouryon recommends a maximum storage temperature ( $T_s$  max.) for each organic peroxide product.

$T_s$ Max.	-20°C (-4°F)
Note	When stored according to these recommended storage conditions, Trigonox SBP will remain within the Nouryon specifications for a period of at least three months after delivery.

## Packaging and transport

Trigonox SBP is packed in non-returnable, one gallon polyethylene containers of 8 lb net weight (4 per case). Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Trigonox SBP is classified as Organic peroxide type C; liquid, temperature controlled; Division 5.2; UN 3113.

## Safety and handling

Keep containers tightly closed. Store and handle Trigonox SBP in a dry well-ventilated place away from sources of heat or ignition and direct sunlight. Never weigh out in the storage room. Avoid contact with reducing agents (e.g. amines), acids, alkalis and heavy metal compounds (e.g. accelerators, driers and metal soaps). Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Trigonox SBP. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at <https://polymerchemistry.nouryon.com>

## Major decomposition products

Carbon dioxide, methane, sec-butyl alcohol, methyl ethyl ketone

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Trigonox is a registered trademark of Nouryon Chemicals B.V. or affiliates in one or more territories

## Contact Us

**Europe, Middle East, India and Africa**  
polymerchemistry.nl@nouryon.com

**Asia Pacific**  
polymerchemistry.ap@nouryon.com

**Americas**  
polymerchemistry.na@nouryon.com

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, orange, sans-serif font.